

FORM PTO 1390
(REV 5-93)

US DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE

ATTORNEY DOCKET NUMBER

2001_0768A

TRANSMITTAL LETTER TO THE UNITED STATES
DESIGNATED/ELECTED OFFICE (DO/EO/US)
CONCERNING A FILING UNDER 35 U.S.C. §371

U.S. APPLICATION NO.
(if known, enter for 1)
NEW 097869042

International Application No.
PCT/NO99/00403

International Filing Date
December 22, 1999

Priority Date Claimed
December 23, 1998

Title of Invention

CATALYSTS CONSISTING OF METALS ON HYDROTALCITE-BASED CARRIER MATERIALS, AND METHOD FOR THE PREPARATION THEREOF

Applicant(s) For DO/EO/US


Unni OLSBYE, Duncan AKPORIAYE, Erling RYTTER, and Morten RØNNEKLEIV

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. §371.
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. §371.
3. ☒ This express request to begin national examination procedures (35 U.S.C. §371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. §371(b) and PCT Articles 22 and 39(1).
4. ☒ A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date.
5. ☒ A copy of the International Application as filed (35 U.S.C. §371(c)(2)) (in English)
 - a. ☐ is transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☒ has been transmitted by the International Bureau.
 - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US)
6. ☐ A translation of the International Application into English (35 U.S.C. §371(c)(2)).
7. ☒ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. §371(c)(3)).
 - a. ☐ are transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☐ have been transmitted by the International Bureau.
 - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
 - d. ☒ have not been made and will not be made.
8. ☐ A translation of the amendments to the claims under PCT Article 19.
9. ☒ An oath or declaration of the inventor(s) (35 U.S.C. §371(c)(4)). (Unexecuted)
10. ☐ A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. §371(c)(5)).

Items 11. to 14. below concern other document(s) or information included:

11. ☒ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
12. ☐ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
13. ☒ A **FIRST** preliminary amendment.
☐ A **SECOND** or **SUBSEQUENT** preliminary amendment.
14. ☒ Other items or information: (a) Form PCT/IB/308; (b) International Search Report; (c) Form PCT/IPEA/416 with attached International Preliminary Examination Report; and (d) Published International Application (WO 00/38832).

U.S. APPLICATION NO. 09/869042 NEW		INTERNATIONAL APPLICATION NO. PCT/NO99/00403		ATTORNEY'S DOCKET NO. 2001 0768A					
15. [X] The following fees are submitted BASIC NATIONAL FEE (37 CFR 1.492(a)(1)-(5)): Neither international preliminary examination fee nor international search fee paid to USPTO and International Search Report not prepared by the EPO or JPO \$1000.00 International Search Report has been prepared by the EPO or JPO \$ 860.00 International preliminary examination fee not paid at USPTO but international search paid to USPTO \$ 710.00 International preliminary examination fee paid to USPTO but claims did not satisfy provisions of PCT Article 33(1)-(4) \$ 690.00 International preliminary examination fee paid at USPTO and all claims satisfied provisions of PCT Article 33(1)-(4) \$ 100.00 ENTER APPROPRIATE BASIC FEE AMOUNT =				<table border="1" style="width:100%; border-collapse: collapse;"> <tr> <th style="width:50%;">CALCULATIONS</th> <th style="width:50%;">PTO USE ONLY</th> </tr> <tr> <td style="height: 100px;"></td> <td></td> </tr> </table>		CALCULATIONS	PTO USE ONLY		
CALCULATIONS	PTO USE ONLY								
Surcharge of \$130.00 for furnishing the oath or declaration later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492(e)).				\$					
Claims	Number Filed	Number Extra	Rate						
Total Claims	75 -20 =	55	X \$18.00	\$990.00					
Independent Claims	2 - 3 =	0	X \$80.00	\$					
Multiple dependent claim(s) (if applicable)			+ \$270.00	\$270.00					
TOTAL OF ABOVE CALCULATIONS =				\$2260.00					
<input type="checkbox"/> Small Entity Status is hereby asserted. Above fees are reduced by 1/2.				\$					
SUBTOTAL =				\$2260.00					
Processing fee of \$130.00 for furnishing the English translation later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492(f)).				\$					
TOTAL NATIONAL FEE =				\$2260.00					
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). \$40 per property +				\$					
TOTAL FEES ENCLOSED =				\$2260.00					
				Amount to be refunded	\$				
				Amount to be charged	\$				
a. [X] A check in the amount of \$2260.00 to cover the above fees is enclosed. A duplicate copy of this form is enclosed. b. <input type="checkbox"/> Please charge my Deposit Account No. 23-0975 in the amount of \$_____ to cover the above fees. A duplicate copy of this sheet is enclosed. c. <input type="checkbox"/> The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. 23-0975.									
NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.									
19. CORRÉSPONDENCE ADDRESS <div style="text-align: center;">  000513 PATENT TRADEMARK OFFICE </div>			By: <u>Michael R. Davis</u> Michael R. Davis, Registration No. 25,134 WENDEROTH, LIND & PONACK, L.L.P. 2033 "K" Street, N.W., Suite 800 Washington, D.C. 20006-1021 Phone: (202) 721-8200 Fax: (202) 721-8250 June 22, 2001						

THE COMMISSIONER IS AUTHORIZED
 TO CHARGE ANY DEFICIENCY IN THE
 FEES FOR THIS PAPER TO DEPOSIT
 ACCOUNT NO. 23-0975

[CHECK NO. 45085]

[2001_0768A]

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re application of :
Unni OLSBYE et al. : Attn: BOX PCT
Serial No. NEW : Docket No. 2001_0768A
Filed June 22, 2001 :

CATALYSTS CONSISTING OF METALS
ON HYDROTALCITE-BASED CARRIER
MATERIALS, AND METHOD FOR THE
PREPARATION THEREOF

[Corresponding to PCT/NO99/00403
Filed December 22, 1999]

PRELIMINARY AMENDMENT

Assistant Commissioner for Patents,
Washington, DC 20231

Sir:

Please amend the above-identified application as follows:

IN THE SPECIFICATION

Page 1, after the title of the invention, please insert:

--This application is a 371 application of PCT/NO99/00403 filed December 22, 1999.--

IN THE CLAIMS

Please amend claims as follows:

4. (Amended) The catalyst of claim 1 or 2, wherein M^{2+} is Mg.
5. (Amended) The catalyst of claim 1 or 2, wherein M^{3+} is Al.
6. (Amended) The catalyst of claim 1 or 2, wherein M^{3+} is further Ga.

7. (Amended) The catalyst of claim 1 or 2, wherein the at least one metal salt or complex has been added in an aqueous solution.

11. (Amended) The catalyst of claim 9, wherein the at least one metal salt or complex has been added in an aqueous inorganic acid solution.

13. (Amended) The catalyst of claim 9, wherein the acid aqueous solution is an aqueous solution of an organic acid.

15. (Amended) The catalyst of claim 1 or 2, wherein the at least one metal salt or complex has been added in an organic solution.

17. (Amended) The catalyst of claim 1 or 2, wherein the at least one metal salt or complex has been added by wet impregnation.

18. (Amended) The catalyst of claim 1 or 2, wherein the contact time between the metal containing solution and the carrier material has been between 0.01 and 30 hours, preferably between 0.05-5 hours.

19. (Amended) The catalyst of claim 1 or 2, wherein the at least one metal salt or complex has been added by incipient impregnation.

20. (Amended) The catalyst of claim 1 or 2, wherein the hydrotalcite based carrier has been subject to preparation by mixing $\text{Mg}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ and $\text{Al}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$ dissolved in water with a basic aqueous solution containing OH and CO_3 anions.

24. (Amended) The catalyst of claim 1 or 2, wherein the hydrotalcite based carrier has been subject to wet impregnation as defined in the claim 17 and anion exchange.

25. (Amended) The catalyst of claim 1 or 2, wherein the hydrotalcite based carrier has been subject to a combination of any of the treatments of the claims 20-24.

26. (Amended) The catalyst of claim 1 or 2, wherein the hydrotalcite based carrier has been calcined at a temperature of 700 to 1200°C, preferably 700-800°C.

27. (Amended) The catalyst of claim 1 or 2, wherein the final catalyst calcination takes place at a temperature of 400 to 1200°C, preferably 560-800°C.

28. (Amended) The catalyst of claim 1 or 2, wherein a binder is admixed.

29. (Amended) The catalyst of claim 2, wherein the hydrotalcite based carrier has been impregnated by at least one metal selected from the group VIII of the periodical table of the elements.

30. (Amended) The catalyst of claim 2, wherein the hydrotalcite based carrier has been impregnated by at least one metal selected from the group IVA of the periodical table of the elements.

33. (Amended) The catalyst of claim 30 or 31, wherein the hydrotalcite based carrier has been impregnated by at least one salt complex of Sn from the group IVA of the periodical table of the elements.

34. (Amended) The catalyst of claim 32, wherein the hydrotalcite based carrier has been impregnated by at least one salt complex of Pt as the group VIII and by at least one salt or complex of Sn as the group IVA of the periodical table of the elements metal.

36. (Amended) The catalyst of claim 29, 31 or 32, wherein the salt of Pt is $\text{H}_2\text{PtCl}_6 \cdot 6\text{H}_2\text{O}$.

37. (Amended) The catalyst of claim 30, 31 or 32, wherein the salt of Sn is $\text{SnCl}_2 \cdot 2\text{H}_2\text{O}$.

38. (Amended) The use of a catalyst of claim 1 or 2 in a catalytic process.
39. (Amended) The use of a catalyst of claim 2 in dehydrogenation reactions.
40. (Amended) The use of a catalyst of claim 2 in the dehydrogenation of alkanes.
41. (Amended) The use of a catalyst of claim 2 in the dehydrogenation of C₂₋₄ alkanes.
42. (Amended) The use of a catalyst of claim 2 in the dehydrogenation of propane.
43. (Amended) The use of a catalyst of claim 2 in the hydrogenation of unsaturated hydrocarbons.

REMARKS


The specification has been amended to insert a cross-reference to the International Application.

The claims have been amended to correct their improper multiple dependency.

Attached hereto is a marked-up version of the changes made to the claims by the current amendment. The attached page is captioned "Version with markings to show changes made."

Respectfully submitted,

Unni OLSBYE et al.

By 
Michael R. Davis
Registration No. 25,134
Attorney for Applicants

MRD/aeH
Washington, D.C. 20006-1021
Telephone (202) 721-8200
Facsimile (202) 721-8250
June 22, 2001

THE COMMISSIONER IS AUTHORIZED
TO CHARGE ANY DEFICIENCY IN THE
FEES FOR THIS PAPER TO DEPOSIT
ACCOUNT NO. 23-0975

VERSION WITH MARKINGS TO SHOW CHANGES MADE

4. (Amended) The catalyst of [the claims 1-3] claim 1 or 2, wherein M^{2+} is Mg.
5. (Amended) The catalyst of [the claims 1-4] claim 1 or 2, wherein M^{3+} is Al.
6. (Amended) The catalyst of [the claims 1-5] claim 1 or 2, wherein M^{3+} is further Ga.
7. (Amended) The catalyst of [the claims 1-6] claim 1 or 2, wherein the at least one metal salt or complex has been added in an aqueous solution.
11. (Amended) The catalyst of [the claims 9 and 10] claim 9, wherein the at least one metal salt or complex has been added in an aqueous inorganic acid solution.
13. (Amended) The catalyst of [the] claim 9 [and 10], wherein the acid aqueous solution is an aqueous solution of an organic acid.
15. (Amended) The catalyst of [the claims 1 and 2] claim 1 or 2, wherein the at least one metal salt or complex has been added in an organic solution.
17. (Amended) The catalyst of [the claim 1 and 2] claim 1 or 2, wherein the at least one metal salt or complex has been added by wet impregnation.
18. (Amended) The catalyst of [the claims 1-17] claim 1 or 2, wherein the contact time between the metal containing solution and the carrier material has been between 0.01 and 30 hours, preferably between 0.05-5 hours.
19. (Amended) The catalyst of [the claims 1 or 2] claim 1 or 2, wherein the at least one metal salt or complex has been added by incipient impregnation.
20. (Amended) The catalyst of [the claims 1-19] claim 1 or 2, wherein the hydrotalcite based carrier has been subject to preparation by mixing $Mg(NO_3)_2 \cdot 6H_2O$ and $Al(NO_3)_3 \cdot 9H_2O$ dissolved in water with a basic aqueous solution containing OH and CO_3 anions.

2001-06-24 09:33:50

24. (Amended) The catalyst of [the claims 1-23] claim 1 or 2, wherein the hydrotalcite based carrier has been subject to wet impregnation as defined in the claim 17 and anion exchange.

25. (Amended) The catalyst of [the claims 1-24] claim 1 or 2, wherein the hydrotalcite based carrier has been subject to a combination of any of the treatments of the claims 20-24.

26. (Amended) The catalyst of [the claims 1-22] claim 1 or 2, wherein the hydrotalcite based carrier has been calcined at a temperature of 700 to 1200°C, preferably 700-800°C.

27. (Amended) The catalyst of [the claims 1-26] claim 1 or 2, wherein the final catalyst calcination takes place at a temperature of 400 to 1200°C, preferably 560-800°C.

28. (Amended) The catalyst of [the claims 1-27] claim 1 or 2, wherein a binder is admixed.

29. (Amended) The catalyst of [the claims 2-28] claim 2, wherein the hydrotalcite based carrier has been impregnated by at least one metal selected from the group VIII of the periodical table of the elements.

30. (Amended) The catalyst of [the claims 2-29] claim 2, wherein the hydrotalcite based carrier has been impregnated by at least one metal selected from the group IVA of the periodical table of the elements.

33. (Amended) The catalyst of [the claims 30 and 31] claim 30 or 31, wherein the hydrotalcite based carrier has been impregnated by at least one salt complex of Sn from the group IVA of the periodical table of the elements.

34. (Amended) The catalyst of [the claims 32 and 33] claim 32, wherein the hydrotalcite based carrier has been impregnated by at least one salt complex of Pt as the group VIII and by at least one salt or complex of Sn as the group IVA of the periodical table of the elements metal.

36. (Amended) The catalyst of [the claims] claim 29, 31 or [and] 32, wherein the salt of Pt is $\text{H}_2\text{PtCl}_6 \cdot 6\text{H}_2\text{O}$.

37. (Amended) The catalyst of [the claims 30-33] claim 30, 31 or 32, wherein the salt of Sn is $\text{SnCl}_2 \cdot 2\text{H}_2\text{O}$.

38. (Amended) The use of a catalyst of [any of the claims 1-37] claim 1 or 2 in a catalytic process.

39. (Amended) The use of a catalyst of [any of the claims 2-37] claim 2 in dehydrogenation reactions.

40. (Amended) The use of a catalyst of [any of the claims 2-37] claim 2 in the dehydrogenation of alkanes.

41. (Amended) The use of a catalyst of [any of the claims 2-37] claim 2 in the dehydrogenation of C_{2-4} alkanes.

42. (Amended) The use of a catalyst of [any of the claims 2-37] claim 2 in the dehydrogenation of propane.

43. (Amended) The use of a catalyst of [any of the claims 2-37] claim 2 in the hydrogenation of unsaturated hydrocarbons.

Catalysts consisting of metals on hydrotalcite-based carrier materials, and method for the preparation thereof.


FIELD OF THE INVENTION

The present invention relates to catalysts. Particularly the invention relates to (de)hydrogenation catalysts. The invention further relates to the processes of preparing such catalysts. The invention also relates to the use of such catalysts in catalytic processes, particularly for the dehydrogenation of paraffins. Further the invention relates to processes of preparing alkenes by the use of such dehydrogenation catalysts, and to the hydrogenation of unsaturated hydrocarbons by the use of such catalysts.

BACKGROUND OF INVENTION

In a previous invention¹, it has been shown that catalysts with excellent activity and stability properties for the catalytic dehydrogenation of light paraffins may be obtained by deposition of a Group VIII metal, a Group IVA metal and, optionally, a Group IA metal, on a mixed oxide carrier material, Mg(Al)O. The mixed oxide carrier material is characterised by a high surface area (typically 100-300 m²/g) and a high stability towards sintering. In a more recent invention², it was shown that improved stability of the carrier material is obtained by increasing the M²⁺/M³⁺ ratio (> 2) and by increasing the calcination temperature (700-1200°C).

Mixed M²⁺(M³⁺)O materials may be obtained by calcination of a hydrotalcite-like material (HTC) of general formula:



at temperatures in the range 350-800°C³. The transformation to the mixed oxide phase may be (partly) reversible, depending on the elements, which constitute the original HTC material, the preparation method, as well as the calcination conditions³. It has been reported that a M²⁺(M³⁺)O material, that had been calcined at 500°C, regained it's hydrotalcite-like structure after contacting it with water^{6,8, 4,5}. It has further been reported that when hydrotalcite-like

materials are used as ion-exchange materials for cleaning cooling water, such materials have a much higher ion uptake capacity when contacted with an aqueous solution after calcination to the oxide structure, than the corresponding uncalcined materials^{4,5}. The explanation that was suggested is that ions present in the aqueous solution are taken up as constituent components in the structure as it is re-converted to the hydrotalcite-like form⁴.

In the literature, numerous examples may be found relating to the use of hydrotalcite-like materials as catalysts or catalyst carriers^{e.g., 3}. Due to its layered structure, hydrotalcite-like materials and the calcined analogs offer a variety of possibilities for insertion of an active metal, or of a promoter compound, as illustrated by the following examples:

- The active metal may be introduced as one of the hydrotalcite cation components, followed by partial decomposition of the structure near the catalyst surface, by which the active metal component is released (e.g. Ni-Al-O compounds for use in steam reforming⁶).
- The active metal may be impregnated on a hydrotalcite-based carrier (e.g. Pt on Mg-Al-O used for aromatisation of n-hexane⁷).
- The active metal may be introduced as anions by anion exchange in the interlayer space (e.g. Mo- or V-containing HTC-based catalysts for the oxidative dehydrogenation of hydrocarbons⁸).

The impregnation methods that have been published to date, and which are relevant for the present invention, may be illustrated by the following examples:

In ⁹, a Ru/Mg(Al)O catalyst is prepared by dissolving RuCl₃ in water and »throwing into the flask in one go» a (Mg-Al-O type) hydrotalcite in the hydroxycarbonate or oxide form. The resulting material is centrifuged, vacuum-dried and, optionally, heat-treated at 500°C in N₂. It is then reduced and used for the hydrogenation of aromatic hydrocarbons at 150°C. In ¹⁰, the invention is extended to involve other platinum group metals, preferably Pd.

In ¹¹, Pt and/or Pd salt is dissolved in a solvent (preferably water), followed by spraying it onto a hydrotalcite support, or (preferably) soaking the hydrotalcite support in the solution. It is underlined that the pH of the solution must be at least about 5 or higher (preferably 6-8), in

order to avoid damage of the hydrotalcite. After the metal deposition step, the product is heated to 200-400°C in an inert or oxidising atmosphere, and reduced at about 50-450°C, before using it as a catalyst for CO oxidation in the temperature range (-60)-400°C.

- 5 In ⁷, a calcined hydrotalcite, Mg(Al)O, is impregnated with Pt(NH₃)₄Cl₂ in aqueous solution, dried, calcined in air at 380°C and reduced in H₂ at 430°C prior to using it as an *n*-hexane aromatisation catalyst at 480°C. A patent corresponding to the said publication covers (in Claim 1) «aromatisation catalysts comprising a Group VIII metal on a hydrotalcite-type support having in its uncalcined form a hydroxycarbonate structure» ¹².

10

15

20

25

In ¹³, Pt/Mg(Al)O catalysts were prepared by various methods and the final materials compared as *n*-hexane aromatisation catalysts. Prior to impregnation, the hydrotalcite was calcined at 600°C for 12-15 hrs. XRD analysis showed diffuse peaks corresponding to MgO after calcination. Impregnation was performed by either incipient wetness impregnation of H₂PtCl₆ from an aqueous solution, leading to re-generation of the HTC structure, by vapour phase impregnation of Pt(acac)₂, or by liquid phase impregnation of Pt(acac)₂ dispersed in acetone. During impregnation of Pt(acac)₂ from vapour phase or from acetone, the MgO structure of the carrier material was maintained. After impregnation, the catalysts were calcined at 350°C/6h and reduced in flowing H₂ at 400°C/2h. During calcination, the MgO phase was partly regenerated for the catalyst impregnated from aqueous solution. H₂ chemisorption measurements showed that vapour impregnation gave twice as high metal dispersion (H/Pt = 1.4) compared to liquid impregnation from aqueous or acetone solution (H/Pt = 0.5). *n*-hexane aromatisation experiments showed that the catalyst prepared from an acidic metal precursor in aqueous solution led to a higher selectivity towards cracking than the other catalysts. This effect was explained by a higher acidity of the metal complex impregnated from aqueous phase. Impregnation of the catalysts with an alkali metal (K) led to improved benzene selectivity.

30

In our group's previous inventions, an organic solvent was used for metal deposition^{1,2}. The choice of an organic solvent was based on two observations:

First, the materials were to be used at elevated temperatures, where the hydrotalcite is known to be transformed to a MgO structure. The high surface area of the calcined carrier material


(typically 100-300 m²/g) compared to the hydrotalcite phase (typically <50 m²/g) was believed to give the best dispersion of the active components (compared to restoration of the hydrotalcite during aqueous impregnation).

Second, the Group IVA metal salt, which is preferably tin in the previous invention¹, was known to have a higher solubility in organic solvents than in water¹⁴. It is known in the art that tin-containing salts may be dissolved in water after the addition of an inorganic acid, or a mixture of an inorganic and an organic acid¹⁵. In the course of the present work, it was discovered that Group IVA metal salts may also be dissolved in water acidified with an organic acid alone. It was further discovered that both aqueous and organic solutions containing Pt and Sn turned red upon dissolution of SnCl₂, indicating the formation of a Pt-Sn complex.

Due to environmental concerns, organic solvents may not be the optimal choice for catalyst preparation at a commercial plant scale. Based on such concerns, the original aim of the present work was to develop a metal deposition method based on aqueous metal salt solutions. Surprisingly, it was found that an aqueous suspension of the M²⁺(M³⁺)O carrier material, leading to the reformation of the hydrotalcite-like phase during metal addition, leads to catalysts with improved activity and stability properties compared to those obtained by metal addition to the calcined M²⁺(M³⁺)O phase.

Under industrial conditions, catalyst pellets of a certain size must be used in order to reduce the pressure drop through the catalyst bed, especially in fixed-bed reactors. In order to increase the mechanical strength of the catalyst pellets, binder materials are often added before pelletisation. Alumina is often used for this purpose.¹⁷

Catalytic dehydrogenation of hydrocarbons is a well-known and commercially important process (16). The reactions follow the general reaction equation:



Dehydrogenation reactions are strongly endothermic, and the conversion is limited by thermodynamic equilibrium. As an example, the equilibrium conversion for the catalytic dehydrogenation of propane is approx. 62% under the conditions used in the present work.

The Gibbs energy of reaction (i) becomes more favorable with increasing temperatures, leading to higher equilibrium conversions. The equilibrium conversion at a given temperature further decreases with increasing pressure, and increases with an increasing chain-length (n). The major byproducts from dehydrogenation reactions are lighter hydrocarbons resulting from cracking reactions, as well as coke. Hydrogenolysis of the reactant, as well as hydrogenation of unsaturated products, may also occur. Coke formation leads to catalyst deactivation through encapsulation of the active site, and coke must be gasified in regeneration cycles. In some cases, steam is added to the process to prevent coke formation. In those cases, CO_x may be formed from steam reforming of the hydrocarbons.

SUMMARY OF INVENTION

This invention relates to a method for preparing catalysts consisting of metals (in any oxidation state) on a M²⁺(M³⁺)O support, where M²⁺ is one or a combination of several divalent cation(s), such as Mg, Ni, Co, Cr, and M³⁺ is one or a combination of several trivalent cation(s), such as Al, Ga, Cr, Co. The said catalyst is obtained by addition of metal(s) to the support while the latter is (at least partly) in, or transformed to, a hydrotalcite phase, followed by washing and calcination to obtain the final catalyst.

Prior to metal deposition, the support material may have been subject to preparation; preparation and drying; preparation, drying and calcination; preparation, drying, calcination and suspension; preparation and anion-exchange, or any other combination of the said methods, as well as any other method known in the art for obtaining a hydrotalcite-like phase.


The metal(s) to be added to the carrier material may exist as organic or inorganic metal salts or complexes, or as a mixture of such salts and complexes. Prior to addition, the metals may or may not be dissolved in an organic solvent, such as ethanol, acetone, or in an aqueous solution. The aqueous solution may have a neutral pH, or it may have been acidified by using an inorganic acid, such as e.g. HCl, HNO₃, or it may have been acidified by using an organic acid, such as e.g. acetic acid, citric acid, oxalic acid; or by using a mixture of organic and inorganic acids.

The solvent may also consist of both an organic solvent and water with or without an organic acid and/or an inorganic acid.

The metal addition may proceed through wet impregnation, incipient wetness impregnation, spraying, vapour deposition or any other method known in the art. The metal addition may take place while the carrier material is in a suspension, or on a dry or wetted carrier material in a fixed bed, a fixed moving bed or a fluidized bed state. Addition of several metals may proceed simultaneously or in a sequential order. When performed simultaneously, the several metals may be present as individual ions, or in mixed complex ions. The wet impregnation contact time may range from 0.01 to 30 hours, preferably about 0.05 to 5 hours.

After the metal addition step, the resulting material is optionally filtered and/or washed and/or dried, and finally heated in an inert or oxidizing atmosphere in order to obtain a catalyst with a high surface area, high sintering resistance and high and stable metal dispersion. Before using it as a catalyst, the material may optionally be treated in a reducing atmosphere under conditions which lead to an optimal oxidation state of the active metal(s).

Thus the present invention particularly relates to a catalyst comprising at least one metal loaded on a hydrotalcite-based carrier material which has the following formula in its uncalcined form



wherein M^{2+} is at least one divalent metal; and M^{3+} is at least one trivalent metal;

A is an n-valent anion

n is 1 or 2,

c is 1 or 2,

and a and b are positive numbers, $a > b$;


the catalyst being prepared by:

a) addition of at least one metal salt or complex to the carrier material, of which the carrier material is (at least partly) in, or transformed to, the hydrotalcite phase during the metal addition step;

b) followed by washing, and

c) calcination.

Particularly the invention relates to a (de)hydrogenation catalyst comprising at least one metal selected from each of the group VIII (group IVA and group IA) of the periodical table of elements loaded on a hydrotalcite-based carrier material which has the following formula in its uncalcined form



wherein M^{2+} is at least one divalent metal; and M^{3+} is at least one trivalent metal;

A is an n-valent anion

n is 1 or 2,

c is 1 or 2

and a and b are positive numbers, $a > b$;

the catalyst being prepared by:

a) addition of at least one metal salt or complex to the carrier material, of which the carrier material is (at least partly) in, or transformed to, the hydrotalcite phase during the metal addition step;

followed by

b) washing, and

c) calcination.

In a preferred embodiment M^{2+} is at least one divalent metal selected from the group

consisting of Mg, Ni, Zn, Fe, Co, Cu, Cr, Mn, Ru, Rh, Pd, Os, Ir, Pt;

and M^{3+} is at least one trivalent metal selected from the group consisting of Al, Ga, Ni, Co, Fe, Cr, Mn, V, Ti;

A is OH and/or CO_3 ; CH_3COO ; or other inorganic or organic acid residues

n is 1 or 2.

Preferably M^{2+} is Mg.

Further M^{3+} is preferably Al.

Optionally M^{3+} is further Ga.

- 5 According to one option the at least one metal salt or complex has been added in an aqueous solution.

In that case the at least one metal salt or complex may have been added in an aqueous neutral solution.

10

Further the at least one metal salt or complex may have been added in an acid aqueous solution.

15

In that case it is preferred that the pH of the acid aqueous solution is lower than 5, and preferably lower than 4.

According to a preferred embodiment thereof the at least one metal salt or complex has been added in an aqueous inorganic acid solution.

20

A preferred aqueous solution is an aqueous HCl solution.

The acid aqueous solution may also be a solution of an organic acid such as acetic acid.

25

Another option is that the at least one metal salt or complex has been added in an organic solution.

The addition of the at least one metal salt or complex has then according to a preferred embodiment been performed in an ethanol solution.

30

According to another option of the invention the at least one metal salt or complex has been added by wet impregnation.

The contact time between the metal containing solution and the carrier material may be between 0.01-30 hours, preferably between 0.05-5 hours.

According to a further option of the invention the at least one metal salt or complex may have been added by incipient impregnation.

The at least one metal salt or complex may also have been added by spraying.

At last the at least one metal salt or complex may further have been added by vapor deposition.

The hydrotalcite based carrier has preferably been prepared by mixing $\text{Mg}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ and $\text{Al}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$ dissolved in water with a basic aqueous solution comprising OH and CO_3 anions.

Further the hydrotalcite based carrier may have been subject to drying.

In addition the hydrotalcite based carrier may have been subject to calcination.

Also the hydrotalcite based carrier may have been subject to the above mentioned preparation, drying and calcination followed by suspension.

The hydrotalcite based carrier may optionally have been subject to an anion exchange.

At last the hydrotalcite based carrier may have been subject to a combination of any of the treatments mentioned above.

The calcination temperature of the hydrotalcite based carrier is preferably in the range of about 700 to 1200 °C, particularly about 700-800°C

The final catalyst calcination takes preferably place at a temperature of about 400 to 1200 °C, particularly about 560- 800°C.

The catalyst may be admixed a binder.

In the case of the (de)hydrogenation catalyst the hydrotalcite based carrier has been
5 impregnated by at least one metal selected from the group VIII of the periodical table of the elements.

Further in a preferred embodiment the hydrotalcite based carrier has been impregnated by at least one metal selected from the group IVA of the periodical table of the elements.

10 Particularly the hydrotalcite based carrier has been impregnated by at least one metal selected from the group VIII, at least one metal selected from the group IVA, and optionally at least one metal selected from the group IA of the periodical table of the elements.

15 Particularly the hydrotalcite based carrier has been impregnated by at least one salt or complex of Pt as the group VIII of the periodical table of the elements metal.

Suitably the hydrotalcite based carrier has been impregnated by at least one salt or complex of Sn from the group IVA of the periodical table of the elements.

20 In a particularly preferred embodiment of the invention the hydrotalcite based carrier has been impregnated by at least one salt or complex of Pt as the group VIII and by at least one salt or complex of Sn as the group IVA of the periodical table of the elements metal.

25 A preferred combination is the one wherein the hydrotalcite based carrier has been impregnated by a salt or complex of Pt and by a salt or complex of Sn.

The preferred salt of Pt is $\text{H}_2\text{PtCl}_6 \cdot 6\text{H}_2\text{O}$.

30 The preferred the salt of Sn is $\text{SnCl}_2 \cdot 2\text{H}_2\text{O}$.

Accordingly a catalyst as defined above is useful in a catalytic process.

When the catalytic metal is Pt the catalyst is particularly useful in dehydrogenation reactions, particularly in the dehydrogenation of alkanes.

- 5 Of particular interest is in the dehydrogenation of C_{2-4} alkanes, such as the dehydrogenation of propane.

Use of the catalyst of the invention for the hydrogenation of unsaturated hydrocarbons is also subject matter of the present invention.

10

DETAILED DESCRIPTION OF INVENTION

The invention is illustrated by the following examples.

General:

Powder X-ray diffraction measurements were performed using a Siemens D-5000 diffractometer with $Cu-K_{\alpha}$ radiation. The specific surface area was measured using nitrogen by the BET method. XRD and BET analysis results are shown in Table 1 and in Figures 1-3.

15
20 Figure 1: X-ray diffractograms of a sample prepared according to Example 2; a) after drying, and b) after calcination.

Figure 2: X-ray diffractograms of a sample prepared according to Example 7; a) after impregnation, and b) after impregnation and calcination.

25

Figure 3: X-ray diffractogram of a sample prepared according to Example 11; a) after impregnation, and b) after impregnation and calcination.

30 Calcination was performed under flowing air (100 Nml/min). The sample was heated with a heating rate of $3^{\circ}C/min$ to the final calcination temperature. The duration of the calcination (at the final calcination temperature) was 15 hours for carrier materials, and 5 hours for catalysts. After completing the calcination, the sample was cooled with a cooling rate of appx. $2^{\circ}C/min$.

Before testing, the catalyst powder was pressed to tablets (5 tons pressure, tablet diameter 24 mm), crushed and sieved to a particle diameter of 0.7-1.0 mm.

5 Catalytic testing in dehydrogenation reactions was performed in a fixed bed titanium reactor. The inner diameter of the reactor was 9 mm. A titanium tube of outer diameter 3 mm was located in the centre of the reactor. The reactor temperature was controlled by a thermocouple placed in the 3 mm tube inside the reactor. The catalyst pellets (appx. 3 g) were placed on a titanium sinter in the reactor. The total pressure in the reactor was 1.1 bar.

10 Product analysis was performed using an on-line Gas Chromatograph.

During propane dehydrogenation (PDH), the reaction temperature was 600°C. The GHSV was 1000 h⁻¹ based on propane, and the reaction gas contained 4.5% hydrogen, 32% propane and 15 remainder steam, on a mole basis. The duration of each test cycle was 24 hours, including regeneration.

Prior to testing, the catalyst was activated *in situ* through an ROR (reduction-oxidation-reduction) treatment at 600°C. The ROR treatment is described in detail in¹.

20 Catalyst regeneration was performed by oxidative treatment using air diluted with nitrogen. The oxygen content was initially 2%, and was increased in a stepwise manner to a final level of 21% (pure air). After regeneration, the catalyst was reduced in flowing hydrogen. Both the regeneration and reduction steps were carried out at 600°C.

25 In the catalytic tests, the selectivity towards propene was generally 97-98%, on mole carbon basis. Conversion data from the tests are shown in Table 2.

Dehydrogenation of other feeds were performed according to the procedure described above, 30 but at different temperatures and pressures:

Ethane dehydrogenation was performed at 600-700°C with a feed ratio: Ethane:H₂:H₂O = 16.5 : 4.5 : 79 on a mole basis, and GHSV = 500 h⁻¹ based on ethane. Iso-Butane dehydrogenation was performed at 570-600°C with a feed ratio: Isobutane : H₂ : H₂O = 32 : 4.5 : 63.5 on a mole basis, and GHSV = 1000h⁻¹ based on isobutane.

- 5 Propene hydrogenation was performed at 550°C and 2 bar pressure, with a feed molar ratio: C₃H₆ : H₂ : H₂O = 23 : 27 : 50. The GHSV was 1000h⁻¹ based on propene.

Example 1. Preparation of HTC carrier material

- 10 a) Nitrate salts of magnesium (Mg(NO₃)₂*6H₂O, 116.35 g) and aluminium (Al(NO₃)₃*9H₂O, 17.01 g) were dissolved in distilled water (500 ml). A second solution was prepared from (NH₄)₂CO₃ (2.18 g) and NH₃ (25%, 21 ml) in distilled water (500 ml). The two solutions were slowly added (dropwise addition with 40 minutes duration) to a common reservoir under continuous stirring. The pH of the solution was kept constant at appx. 8, and the temperature was appx. 60°C. The final adduct was filtered, washed with distilled water to neutrality, and dried overnight (100°C). The X-ray diffractogram showed a major hydrotalcite phase.
 - 15 b) A part of the product was subject to calcination at 700°C. The transformation of the hydrotalcite phase into a Mg(Al)O structure was shown by XRD.
- Chemical analysis of the resulting carrier material showed that it had a molar ratio: Mg/Al = 3.

Example 2. Preparation of HTC carrier material

- 25 a) Nitrate salts of magnesium (Mg(NO₃)₂*6H₂O, 233.24 g) and aluminium (Al(NO₃)₃*9H₂O, 34.02 g) were dissolved in distilled water (1000 ml). A second solution was prepared from Na₂CO₃ (4.80 g) and NaOH (45.31 g) in distilled water (1000 ml). The two solutions were slowly added (dropwise addition with 55 minutes duration) to a common reservoir under continuous stirring. The pH of the solution was kept constant at appx. 10, and the temperature was appx. 60°C. The final adduct was filtered, washed with distilled water to neutrality, and dried overnight (100°C). The X-ray diffractogram showed a major hydrotalcite phase.
- 30 b) A part of the product was subject to calcination at 800°C. The transformation of the hydrotalcite phase into a Mg(Al)O structure was shown by XRD.

Chemical analysis of the resulting carrier material, obtained during repeated preparations, showed that it had a molar ratio in the range $\text{Mg/Al} = 5.0 \pm 0.6$. The carrier material used for metal addition had a Mg/Al ratio of 4.8.

XRD patterns of the dried and calcined materials are shown in Figure 1.

5

Example 3. Impregnation of a calcined HTC carrier material from an ethanol solution

a) A Mg-Al-O carrier material (61.95 g) prepared according to Example 1b was co-impregnated with $\text{H}_2\text{PtCl}_6 \cdot 6\text{H}_2\text{O}$ (0.4930 g) and $\text{SnCl}_2 \cdot 2\text{H}_2\text{O}$ (1.4133 g) in ethanol solution (500 ml). The solution was stirred with the carrier material for 2 hours, and the solvent
10 evaporated under reduced pressure. The solid material was then dried (100°C). Part of the material was calcined at 560°C and tested under PDH conditions.

b) A Mg-Al-O carrier material (51.86 g) prepared according to Example 2b was co-impregnated with $\text{H}_2\text{PtCl}_6 \cdot 6\text{H}_2\text{O}$ (0.3889 g) and $\text{SnCl}_2 \cdot 2\text{H}_2\text{O}$ (1.1828 g) in ethanol solution
15 (400 ml). The solution was stirred with the carrier material for 2 hours, and the solvent evaporated under reduced pressure. The solid material was then dried (100°C). Part of the material was calcined at 560°C and tested under PDH conditions.

Example 4. Impregnation of a calcined HTC carrier material from an aqueous solution acidified by HCl, without washing

Tin chloride ($\text{SnCl}_2 \cdot 2\text{H}_2\text{O}$, 0.3181 g) was dissolved in HCl (2M, 51 ml). Hexachloroplatinum ($\text{H}_2\text{PtCl}_6 \cdot 6\text{H}_2\text{O}$, 0.1045 g) was dissolved in distilled water (91 ml). The two solution were mixed. A Mg-Al-O carrier material (13.9 g) prepared according to Example 1b was stirred with the salt solution for 30 minutes. The solution was then filtered, and the solid material
20 dried (100°C). The material was calcined at 560°C and tested under PDH conditions.

Example 5. Impregnation of a calcined HTC carrier material from an aqueous solution acidified by HCl

Tin chloride ($\text{SnCl}_2 \cdot 2\text{H}_2\text{O}$, 0.3398 g) was dissolved in HCl (1M, 109 ml).
30 Hexachloroplatinum ($\text{H}_2\text{PtCl}_6 \cdot 6\text{H}_2\text{O}$, 0.1116 g) was dissolved in distilled water (40 ml). The two solutions were mixed. A Mg-Al-O carrier material (14.88 g) prepared according to Example 1b was stirred with the salt solution for 30 minutes. The solution was then filtered,

and washed 3 times with water (appx. 750 ml). The solid material was dried (100°C). Part of the material was calcined (560°C) and tested under PDH conditions.

Example 6. Impregnation of a calcined HTC carrier material from an aqueous solution acidified by HCl

Tin chloride ($\text{SnCl}_2 \cdot 2\text{H}_2\text{O}$, 0.2429 g) was dissolved in HCl (37%, 6.5 ml).

Hexachloroplatinum ($\text{H}_2\text{PtCl}_6 \cdot 6\text{H}_2\text{O}$, 0.0793 g) was dissolved in distilled water. The two solutions were mixed and distilled water added to a total volume of 100 ml. The solution was mixed with a calcined $\text{Mg}(\text{Al})\text{O}$ material, prepared according to Example 2b (10.6 g). The suspension was stirred for 1 hour, filtered, washed and dried overnight (100°C). The product was then calcined (560°C) and tested under PDH conditions.

Example 7. Impregnation of a calcined HTC carrier material in suspension, from an aqueous solution acidified by HCl (rapid addition)

Tin chloride ($\text{SnCl}_2 \cdot 2\text{H}_2\text{O}$, 0.2482 g) was dissolved in HCl (2M, 32 ml). Hexachloroplatinum ($\text{H}_2\text{PtCl}_6 \cdot 6\text{H}_2\text{O}$, 0.082 g) was dissolved in distilled water (5 ml). The two solutions were mixed. $\text{Mg}(\text{Al})\text{O}$ (10.9 g), prepared according to Example 2b, was slurried in distilled water (60 ml). The suspension was stirred for some minutes, before the salt solution was rapidly added. The final suspension was stirred for 1 hour, filtered, washed and dried overnight (100°C). The product was then calcined (560°C) and tested under PDH conditions.

XRD patterns of the dried and calcined materials are shown in Figure 2.

Example 8. Impregnation of a calcined HTC carrier material in suspension, from an aqueous solution acidified by HCl (dropwise addition)

Tin chloride ($\text{SnCl}_2 \cdot 2\text{H}_2\text{O}$, 0.2094 g) was dissolved in HCl (37%, 5.6 ml).

Hexachloroplatinum ($\text{H}_2\text{PtCl}_6 \cdot 6\text{H}_2\text{O}$, 0.0691 g) was dissolved in distilled water (10 ml). The two solution were mixed, and distilled water added to a total volume of 35 ml. $\text{Mg}(\text{Al})\text{O}$ (9.18 g), prepared according to Example 2b, was added to distilled water (85 ml). The suspension was stirred for some minutes, before the salt solution was added in a dropwise manner (10 min). The final suspension was stirred for 1 hour, filtered, washed and dried (100°C). The product was then calcined (560°C) and tested under PDH conditions. In the main test (Ex. 8a),

the ordinary pretreatment procedure was used, while in a second test (Ex. 8b), a slightly modified pretreatment procedure was used.

Example 9. Impregnation of a calcined HTC carrier material in suspension, from an aqueous solution acidified by HCl, with prolonged contact time

Tin chloride ($\text{SnCl}_2 \cdot 2\text{H}_2\text{O}$, 0.2349 g) was dissolved in HCl (37%, 6 ml). Hexachloroplatinum ($\text{H}_2\text{PtCl}_6 \cdot 6\text{H}_2\text{O}$, 0.0774 g) was dissolved in distilled water (5 ml). The two solution were mixed, and distilled water added to a total volume of 45 ml. $\text{Mg}(\text{Al})\text{O}$ (10.3 g), prepared according to Example 2b, was added to distilled water (55 ml). The suspension was stirred for some minutes, before the salt solution was added in a dropwise manner (4-5 min). The final suspension was stirred for 3 hours, filtered, washed and dried overnight (100°C). The product was then calcined (560°C) and tested under PDH conditions.

Example 10. Impregnation of a calcined HTC carrier material in suspension, from an aqueous solution acidified by HCl, without washing

Tin chloride ($\text{SnCl}_2 \cdot 2\text{H}_2\text{O}$, 0.2015 g) was dissolved in HCl (37%, 5.5 ml). Hexachloroplatinum ($\text{H}_2\text{PtCl}_6 \cdot 6\text{H}_2\text{O}$, 0.0670 g) was dissolved in distilled water (10 ml). The two solution were mixed, and distilled water added to a total volume of 40 ml. $\text{Mg}(\text{Al})\text{O}$ (8.83 g), prepared according to Example 2b, was added to distilled water (45 ml). The suspension was stirred for some minutes, before the salt solution was added in a dropwise manner (10 min). The final suspension was stirred for 1 hour, filtered and dried overnight (100°C). The product was then calcined (560°C) and tested under PDH conditions.

Example 11. Impregnation of a calcined HTC carrier material in suspension, from an aqueous solution acidified by acetic acid

Tin chloride ($\text{SnCl}_2 \cdot 2\text{H}_2\text{O}$, 0.2355 g) and hexachloroplatinum ($\text{H}_2\text{PtCl}_6 \cdot 6\text{H}_2\text{O}$, 0.076 g) were dissolved in acetic acid (10 ml). Distilled water was added to a total volume of 50 ml. $\text{Mg}(\text{Al})\text{O}$ (10.2 g), prepared according to Example 2b, was added to distilled water (60 ml). The suspension was stirred for some minutes, before the salt solution was added in a dropwise manner (4-5 min). The final suspension was stirred for 0.5 hours, filtered and dried overnight (100°C). XRD of the dried product showed the appearance of a poorly crystalline hydrotalcite. The $d(001)$ value had been shifted to 10.82, indicating that the anion interlayer contains

acetate anions, (Figure 3a). The product was then calcined at 560°C, yielding the MgO phase (Figure 3b).

Example 12. Impregnation of an uncalcined HTC carrier material in suspension, from an aqueous solution acidified by HCl

a) Tin chloride ($\text{SnCl}_2 \cdot 2\text{H}_2\text{O}$, 0.2046 g) was dissolved in HCl (37%, 6.0 ml). Hexachloroplatinum ($\text{H}_2\text{PtCl}_6 \cdot 6\text{H}_2\text{O}$, 0.0677 g) was dissolved in distilled water (10 ml). The two solution were mixed, and distilled water added to a total volume of 40 ml. Mg-Al HTC (14.7 g), prepared according to Example 2a, was added to distilled water (50 ml). The suspension was stirred for some minutes, before the salt solution was added in a dropwise manner (10 min). The final suspension was stirred for 1 hour, filtered, washed and dried overnight (100°C). Part of the product was then calcined (560°C) and tested under PDH conditions.

b) Part of the dried product was calcined at 800°C and tested under PDH conditions.

Example 13. Impregnation of an uncalcined HTC carrier material from an EtOH solution

Tin chloride ($\text{SnCl}_2 \cdot 2\text{H}_2\text{O}$, 0.1779 g) and hexachloroplatinum ($\text{H}_2\text{PtCl}_6 \cdot 6\text{H}_2\text{O}$, 0.0586 g) were dissolved in ethanol (75 ml). The solution were added to a Mg-Al HTC (12.78 g) carrier, prepared according to Example 2a. The suspension was stirred for 2 hours, and the solvent evaporated under reduced pressure. The solid material was dried (100°C), calcined (560°C) and tested under PDH conditions.

Example 14. Preparation of hydrotalcite material containing Mg and Ga, with subsequent impregnation

Nitrate salts of magnesium ($\text{Mg}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$, 73.80 g) and gallium ($\text{Ga}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$, 13.411 g) were dissolved in distilled water (750 ml). A second solution was prepared from K_2CO_3 (3.355 g) and KOH (22.57 g) in distilled water (750 ml). Distilled water (300 ml) was added to a reservoir and heated to 50°C. The two solutions were added to this reservoir in a dropwise manner (total duration 40 minutes) under continuous stirring. The pH of the solution was kept constant at appx. 10, and the temperature was appx. 45°C. The final adduct was filtered,

washed with distilled water and dried overnight (100°C). The X-ray diffractogram showed a hydrotalcite phase.

Part of the material was calcined (800°C) and impregnated with Pt and Sn according to Example 8.

5

Example 15. Impregnation of a wet, uncalcined HTC carrier material in suspension, from an aqueous solution acidified by HCl

a) Tin chloride ($\text{SnCl}_2 \cdot 2\text{H}_2\text{O}$, 0.2046 g) was dissolved in HCl (37%, 6.0 ml).

Hexachloroplatinum ($\text{H}_2\text{PtCl}_6 \cdot 6\text{H}_2\text{O}$, 0.0677 g) was dissolved in distilled water (10 ml). The two solution were mixed, and distilled water added to a total volume of 40 ml. Mg-Al HTC (14.7 g) was prepared according to Example 2a, but without drying. The salt solution was added to the wet carrier material in a dropwise manner (10 min). The final suspension was stirred for 1 hour, filtered, washed and dried overnight (100°C). Part of the product was then calcined (560°C) and tested under PDH conditions.

b) Part of the dried product was calcined at 800°C and tested under PDH conditions.

Example 16. Catalyst testing of the carrier material

A carrier material prepared according to Example 1b was subject to a catalytic test under PDH conditions. GC analysis of the effluent gas showed negligible propane conversion (<1%) under the test conditions described above («General»), but with shorter residence time ($\text{GHSV} = 2400 \text{ h}^{-1}$).

Example 17. Catalyst testing

The catalysts prepared according to Examples 3-15 and 20 were subject to catalytic testing under PDH conditions. Test results obtained during the first 10 test cycles are shown in Table 2.

Example 18. Catalyst testing with other feedstocks

a) Ethane dehydrogenation. A catalyst prepared according to Example 8 was used as an ethane dehydrogenation catalyst (See «General» for test conditions). The results obtained during six subsequent test cycles at 650°C showed a stable activity from cycle to cycle, with an initial conversion of 40%, decreasing to 30% at the end of each test cycle. The

selectivity towards ethene was 80-85%, on mole carbon basis. Before testing as an ethane dehydrogenation catalyst, the catalyst had been subject to PDH testing at 600°C.

- b) Isobutane dehydrogenation. A catalyst prepared according to Example 8 was used as an isobutane dehydrogenation catalyst (See «General» for test conditions). The results obtained during three subsequent test cycles at 590°C showed a rather stable activity from cycle to cycle, with an initial conversion of 58% (Cycle 1), 57% (Cycle 2) and 56% (Cycle 3), decreasing to 44% at the end of each test cycle. The selectivity towards butenes was 96%, on mole carbon basis. Before testing as an isobutane dehydrogenation catalyst, the catalyst had been subject to PDH testing at 600 °C.
- c) Propene hydrogenation. A catalyst prepared according to Example 12 was used as a propene hydrogenation catalyst (See "General" for test conditions). The catalyst had a high initial activity (74% conversion), decreasing to 32% during the first test cycle. The propane selectivity was 98-99% throughout the test.

Example 19. Catalyst calcination

A catalyst prepared according to Example 8 was subject to calcination at various temperatures (560-800°C). Relative Pt dispersion values of the calcined samples were determined by CO pulse chemisorption experiments using an Alta-Mira apparatus (AMI-1) and the ROR pretreatment procedure. The results of the CO pulse chemisorption experiments are shown in Table 3. XRD showed a major MgO phase for all samples, and the BET area was in the range 150-200 m²/g for all samples (Table 1). PDH testing gave very similar results for the samples calcined at 560, 700 and 800°C (Table 2). It should be noted that these results are not directly comparable with the other results in Table 2, due to a slightly modified pretreatment procedure.

Example 20. Addition of binder

A catalyst was prepared according to Example 8, and subsequently mixed with alumina, before pressing, crushing, sieving and testing as a PDH catalyst. The results shown in Table 2 correspond to an alumina content of appx. 20wt%. Similar test results were obtained with other alumina contents.

Table 1: Characterisation results for the materials described in the Examples.

Material	Treatment	BET surface area (m ² /g)	XRD
Ex. 2a	Before calc.	43	HTC
Ex. 2b	After calc.	145	MgO
Ex.3a	Before calc.	n.m.	MgO
Ex.3a	After calc.	202	MgO
Ex.3b	After calc.	123	MgO
Ex.4	After calc.	129	
Ex. 5	After calc.	162	MgO
Ex.6	After calc.	112	MgO
Ex.7	After calc.	113-126	MgO
Ex.8	After calc.	153	MgO
Ex.9	After calc.	106	
Ex.10	After calc.		MgO
Ex.11	After calc.	111	MgO
Ex.12a	After calc.		
Ex.13	After calc.	156	MgO
Ex.14	Before imp.	135	MgO (spinel)
Ex.14	After imp.and calc.	110	MgO (spinel)
Ex.15a	After calc.	172	MgO
Ex.15b	After calc.	121	MgO
Ex.19	Calcined 560/2	180	MgO
Ex.19	Calcined 700/15	184	MgO
Ex.19	Calcined 800/15	160	MgO

Abbreviations:

5 n.m.) Not measured

Table 2: Test results obtained with catalysts described in the Examples.

Catalyst	Cycle 1 conversion		Cycle 3 conversion		Cycle 5 conversion		Cycle 10 conversion	
	Initial	Final	Initial	Final	Initial	Final	Initial	Final
Ex.3a	n.m.	n.m.	62	38	54	33	n.m.	n.m.
Ex.3a	53	35	46	30	n.m.	n.m.	n.m.	n.m.
Ex.3b	18	22	33 ^{II} 31 ^{III}	24 ^{II} 22 ^{III}	n.m.	n.m.	n.m.	n.m.
Ex.4	68	47	59	43	46	32	n.m.	n.m.
Ex.5	59	48	57	45	55 ^I	38 ^I	55	39
Ex.6	55	43	61	44	60	40	60	36
Ex.7	51	42	60	42	59	41	59	39
Ex.8a	50	33	60	45	60	44	60	41
Ex.8b	58	46	n.m.	n.m.	51	47	n.m.	n.m.
Ex.9	54	48	55	41	54	48	n.m.	n.m.
Ex.10	38	24	35	23	35	23	n.m.	n.m.
Ex.11	52	47	52	40	51	38	n.m.	n.m.
Ex.12a	47	38	n.m.	50	58	47	55	40
Ex. 12b	57	45	55	42	55	41	52	38(9 th)
Ex. 13	52	48	53	45	n.m.	n.m.	49	40
Ex.14	59	40	55	31	58	28	n.m.	n.m.
Ex.15a	54	42	49	36	45	32	n.m.	n.m.
Ex. 15b	57	46	55	45	n.m.	n.m.	n.m.	n.m.
Ex. 19 / 560°C	66	38	67	40	66	43	n.m.	n.m.
Ex. 19 / 700°C	65	36	66	37	65	39	65	42
Ex. 19 / 800°C	59	35	61	41	65	41	63	44
Ex.20	55	23	57	29	56	30	n.m.	n.m.

Abbreviations:

5 n.m.) Not measured

ⁱ⁾ Test cycle 6 (due to analytical problems)

ⁱⁱ⁾ Test cycle 2

ⁱⁱⁱ⁾ Test cycle 3

5 Table 3. Influence of calcination temperature on metal dispersion (Example 19)

Calcination temperature (duration) (°C) (hours)	Relative metal dispersion
560 (2)	1.0
560 (15)	1.0
700	1.4
800	1.6

DISCUSSION

10 The characterisation results shown in Figures 1-3 and in Table 1 illustrate that when contacting a calcined hydrotalcite-based material with an aqueous solution, the hydrotalcite phase is regained. After subsequent calcination, the hydrotalcite phase transforms to the oxide phase.

15 However, when contacting a calcined hydrotalcite-based material with an ethanol solution, the oxide structure is maintained.

It has previously (See: «General») been stated that the selectivity of the catalysts prepared according to the present invention, is very high. The major focus of this discussion is therefore on the activity and stability of dehydrogenation catalysts prepared according to the present invention. From the results in Table 2, it is observed that the initial conversion level of the catalysts is generally high during propane dehydrogenation (appx. 60%), and very close to the thermodynamic equilibrium conversion under these conditions. When discussing the catalyst stability, focus is therefore put on the activity at the end of each test cycle, denoted «Final conversion» in Table 2. When reporting that the catalyst reaches a stable performance level, this means that it's final conversion is similar for several consecutive test cycles.

In general, the test results (Table 2) illustrate that the catalysts prepared according to the present invention (i.e.; metal addition, washing and calcination) reach a stable performance level between the 5th and 10th test cycle.

5 The test results shown in Table 2 further illustrate that catalysts prepared according to our previous invention¹ (i.e.; oxide phase of carrier material during metal addition, Example 3), have a life time stability and/or a stable performance level which is clearly inferior to that obtained for samples prepared according to the present invention (i.e.; hydrotalcite phase during metal addition, preferably followed by washing, e.g. Examples 5-9). This means that it
10 is important to add the metal(s) to the hydrotalcite phase, and then calcine it at the desired temperature. Table 2 further illustrates the strong influence of the washing step on the stable performance level of each catalyst (Example 4 vs. Example 5; and Example 8 vs. Example 10). The same trends are observed regardless of the Mg/Al ratio of the hydrotalcite-based carrier material.

15 The metal addition procedure (dry or wet carrier, dropwise or »one go« metal addition, carrier – metal solution contact time) has only a minor influence on the catalyst's initial activity and life time stability.

20 The characterisation results shown in Table 1 and 3 illustrate that the final calcination temperature may be varied compared to the standard calcination temperature (560°C), while maintaining a high metal dispersion and high specific surface area. The corresponding test results (Table 2) illustrate that the calcination of the final catalysts at temperatures above 560°C leads to catalysts with maintained or improved long-term stability.

25 The results in Table 2 further indicate that the impregnation of an uncalcined hydrotalcite, which is subsequently calcined at 560°C, gives a catalyst with a lower deactivation rate within each test cycle, but with a lesser long-term stability compared to catalysts based on pre-calcined carrier materials.

30 Replacing Al in the hydrotalcite phase with Ga does not lead to an improved catalyst compared to carrier materials containing only Mg and Al.

Addition of an alumina binder leads to a more rapid deactivation during each test cycle, but does not alter the long-time stability of the catalyst.

- 5 The use of a modified pretreatment procedure (Ex. 8b (and Ex. 19) compared to Ex. 8a) gave a higher conversion in the first test cycle, but did not alter the long-term stability of the catalyst.

- 10 The dehydrogenation tests using other feedstocks than propane (Example 18) illustrate that the excellent activity and stability properties observed for the catalysts of the present invention, are properties which are of general validity to all types of hydrocarbon dehydrogenation reactions. It is further observed that the catalysts of the present invention are also excellent catalysts for the hydrogenation of unsaturated compounds (Example 18). The particular benefits thus obtained by using the catalysts of the present invention were not to be
15 expected in view of the prior art comprising the references as listed below.

References:


1. Akporiaye, D.; Rønnekleiv, M.; Hasselgård, P.; to Statoil; PCT/NO94/00102
5 (1994), (22 pp).
2. Rytter, E.; Akporiaye, D.; Olsbye, U.; to Statoil; Norwegian Patent Application no. 1998.1126, (1998).
3. Cavani, F.; Trifirò, F.; Vaccari, A.; Cat. Today, 11(2), (1991), 171-301.
4. Miyata, S.; Iijima, N.; Manabe, T.; to Kyowa Chemical Industry Co.;
10 EP 0 152 010 B1, (1985), (10 pp).
5. Sato, T.; Wakabayashi, T.; Shimada, M.; Ind. Eng. Chem. Prod. res.; 25, (1986), 89-92.
6. Clause, O., Gazzano, M, Trifiro, F., Vaccari, A and Zatorski, L., Appl. Cat., 73,
(1991), 217.
7. Davis, R.J, and Derouane, E.G.; Nature, 349, (1991), 313-315.
8. Drezdson, M.A.; Moore, E.J.; Kaminsky, M.P.; to Amoco Corp.; USP 4,843,168,
15 (1989), (8 pp).
9. Fukuhara, H.; Matsunaga, F.; Nakashima, Y.; to Mitsui Petrochemical Industries Ltd.; EP 0 323 192 B1; (1988), (7 pp).
10. Matsunaga, F.; Fukuhara, H.; to Mitsui Petrochemical Industries Ltd.;
20 EPA 0 332 380 A2; (1989), (4 pp).
11. Delzer, G.A.; Kolts, J.H.; to Phillips Petroleum Company; EPA 0 330 224 A1,
(1989), (6 pp).
12. Derouane, E.; Davis, R.J.; Blom, N.J.; to Haldor-Topsoe; EP 0 476 489 B1,
25 (1991), (13 pp).
13. Davis, R.J.; Mielczarski, E.; in: «Selectivity in Catalysis»; Am. Chem. Soc.;
(1993), 327-336.
14. CRC Handbook of Chemistry and Physics, 62nd Ed.; CRC Press, Florida, (1981-82).
15. Khare, G.D.; Porter, R.A.; to Phillips Petroleum Company; USP 5,430,220,
30 (1994); (6 pp).
16. Bariås, O.A.: «Transient kinetic investigation of catalytic dehydrogenation of propane», Ph. D. Thesis, NTH, Inst. For Industrial Chemistry, Trondheim, (1993).

17. Misra, C.: US Patent No. 4,656,156 (1987), 9 pp.

Introduction

PATENT CLAIMS

1. A catalyst comprising at least one metal loaded on a hydrotalcite-based carrier material which has the following formula in it's uncalcined form



wherein M^{2+} is at least one divalent metal; and M^{3+} is at least one trivalent metal;

A is an n-valent anion

n is 1 or 2,


c is 1 or 2,

and a and b are positive numbers, $a > b$;

the catalyst being prepared by:

- a) addition of at least one metal salt or complex to the carrier material, of which the carrier material is (at least partly) in, or transformed to, the hydrotalcite phase during the metal addition step;
- b) followed by washing, and
- c) calcination.

2. A (de)hydrogenation catalyst comprising at least one metal selected from the group VIII of the periodical table of elements loaded on a hydrotalcite-based carrier material which has the following formula in it's uncalcined form



wherein M^{2+} is at least one divalent metal; and M^{3+} is at least one trivalent metal;

A is an n-valent anion

n is 1 or 2,

c is 1 or 2,

and a and b are positive numbers, $a > b$;

the catalyst being prepared by:

a) addition of at least one metal salt or complex to the carrier material, of which the carrier material is (at least partly) in. or transformed to, the hydrotalcite phase during the metal addition step;

followed by

b) washing, and

c) calcination.

3. The catalyst of Claim 1 or 2, wherein M^{2+} is at least one divalent metal selected from the group consisting of Mg, Ni, Zn, Fe, Co, Cu, Cr, Mn, Ru, Rh, Pd, Os, Ir, Pt;

and M^{3+} is at least one trivalent metal selected from the group consisting of Al, Ga, Ni, Co, Fe, Cr, Mn, V, Ti;

A is OH and/or CO_3 ; CH_3COO ; or other inorganic or organic acid residues

n is 1 or 2.

4. The catalyst of the claims 1 - 3, wherein M^{2+} is Mg.

5. The catalyst of the claims 1 - 4, wherein M^{3+} is Al.

6. The catalyst of the claims 1 - 5, wherein M^{3+} is further Ga.

7. The catalyst of the claims 1 - 6, wherein the at least one metal salt or complex has been added in an aqueous solution.

8. The catalyst of claim 7, wherein the at least one metal salt or complex has been added in a neutral aqueous solution.

9. The catalyst of the claim 7, wherein the at least one metal salt or complex has been added in an acid aqueous solution.

10. The catalyst of the claim 9, wherein the pH of the acid aqueous solution is lower than 5, and preferably lower than 4.
11. The catalyst of the claims 9 and 10, wherein the at least one metal salt or complex has been added in an aqueous inorganic acid solution.
12. The catalyst of the claim 11, wherein the addition of the at least one metal salt or complex has been performed in an aqueous HCl solution.
13. The catalyst of the claim 9 and 10, wherein the acid aqueous solution is an aqueous solution of an organic acid.
14. The catalyst of the claim 13, wherein the organic acid is acetic acid.
15. The catalyst of the claims 1 and 2, wherein the at least one metal salt or complex has been added in an organic solution.
16. The catalyst of claim 15, wherein the addition of the at least one metal salt or complex has been performed in an ethanol solution.
17. The catalyst of the claim 1 and 2, wherein the at least one metal salt or complex has been added by wet impregnation.
18. The catalyst of the claims 1-17, wherein the contact time between the metal containing solution and the carrier material has been between 0.01 and 30 hours, preferably between 0.05-5 hours.
19. The catalyst of the claims 1 and 2, wherein the at least one metal salt or complex has been added by incipient impregnation.

20. The catalyst of the claims 1 - 19, wherein the hydrotalcite based carrier has been subject to preparation by mixing $\text{Mg}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ and $\text{Al}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$ dissolved in water with a basic aqueous solution containing OH and CO_3 anions.

5 21. The catalyst of the claim 20, wherein the hydrotalcite based carrier has been subject to preparation as defined in the claim 1 - 20 and drying.

22. The catalyst of the claim 21, wherein the hydrotalcite based carrier has been subject to preparation and drying as defined in the claim 24 and calcination.

10

23. The catalyst of the claims 22, wherein the hydrotalcite based carrier has been subject to preparation, drying and calcination as defined in the claim 25 followed by suspension.

15

24. The catalyst of the claims 1 - 23, wherein the hydrotalcite based carrier has been subject to wet impregnation as defined in the claim 17 and anion exchange.

25. The catalyst of the claims 1 - 24, wherein the hydrotalcite based carrier has been subject to a combination of any of the treatments of the claims 20 - 24.

20

26. The catalyst of the claims 1 - 22, wherein the hydrotalcite based carrier has been calcined at a temperature of 700 to 1200 °C, preferably 700-800°C.

27. The catalyst of the claims 1 - 26, wherein the final catalyst calcination takes place at a temperature of 400 to 1200 °C, preferably 560-800°C.

25

28. The catalyst of the claims 1-27, wherein a binder is admixed.

29. The catalyst of the claims 2 - 28, wherein the hydrotalcite based carrier has been impregnated by at least one metal selected from the group VIII of the periodical table of the elements.

30

30. The catalyst of the claims 2 - 29, wherein the hydrotalcite based carrier has been impregnated by at least one metal selected from the group IVA of the periodical table of the elements.

5 31. The catalyst of the claim 30, wherein the hydrotalcite based carrier has been impregnated by at least one metal selected from the group VIII, at least one metal selected from the group IVA, and optionally at least one metal selected from the group IA of the periodical table of the elements.

10 32. The catalyst of the claim 29, wherein the hydrotalcite based carrier has been impregnated by at least one salt or complex of Pt as the group VIII of the periodical table of the elements metal.

15 33. The catalyst of the claims 30 and 31, wherein the hydrotalcite based carrier has been impregnated by at least one salt or complex of Sn from the group IVA of the periodical table of the elements.

20 34. The catalyst of the claims 32 and 33, wherein the hydrotalcite based carrier has been impregnated by at least one salt or complex of Pt as the group VIII and by at least one salt or complex of Sn as the group IVA of the periodical table of the elements metal.

35. The catalyst of the claim 34, wherein the hydrotalcite based carrier has been impregnated by a salt or complex of Pt and by a salt or complex of Sn.

25 36. The catalyst of the claims 29, 31 and 32, wherein the salt of Pt is $\text{H}_2\text{PtCl}_6 \cdot 6\text{H}_2\text{O}$.

37. The catalyst of the claims 30 - 33, wherein the salt of Sn is $\text{SnCl}_2 \cdot 2\text{H}_2\text{O}$.

38. The use of a catalyst of any of the claims 1 - 37 in a catalytic process.

30 39. The use of a catalyst of any of the claims 2 - 37 in dehydrogenation reactions.

41. The use of a catalyst of any of the claims 2 – 37 in the dehydrogenation of C₂₋₄ alkanes.

5 42. The use of a catalyst of any of the claims 2 – 37 in the dehydrogenation of propane.

43. The use of a catalyst of any of the claims 2 – 37 in the hydrogenation of unsaturated hydrocarbons.

[illegible]

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

1/6






FIGURE 1a

09/869042

2/6





4/6




FIGURE 2b




FIGURE 3a

6/6




FIGURE 3b

09869042

DECLARATION AND POWER OF ATTORNEY FOR U.S. PATENT APPLICATION

(X) Original () Supplemental () Substitute () PCT () DESIGN

As a below named inventor, I hereby declare that: my residence, post office address and citizenship are as stated below next to my name; that I verily believe that I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural inventors are named below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

Title: CATALYSTS CONSISTING OF METALS ON HYDROTALCITE-BASED CARRIER MATERIALS, AND METHOD FOR THE PREPARATION THEREOF

of which is described and claimed in:

() the attached specification, or
 () the specification in application Serial No. NEW, filed June 22, 2001, and with amendments through _____, or
 (X) the specification in International Application No. PCT/NO99/00403, filed December 22, 1999, and as amended on _____ (if applicable).

I hereby state that I have reviewed and understand the content of the above-identified specification, including the claims, as amended by any amendment(s) referred to above.

I acknowledge my duty to disclose to the Patent and Trademark Office all information known to me to be material to patentability as defined in Title 37, Code of Federal Regulations, §1.56.

I hereby claim priority benefits under Title 35, United States Code, §119 (and §172 if this application is for a Design) of any application(s) for patent or inventor's certificate listed below and have also identified below any application for patent or inventor's certificate having a filing date before that of the application on which priority is claimed:

COUNTRY	APPLICATION NO.	DATE OF FILING	PRIORITY CLAIMED
Norway	1998 6116	December 23, 1998	yes

I hereby claim the benefit under Title 35, United States Code §120 of any United States application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35, United States Code §112, I acknowledge the duty to disclose information material to patentability as defined in Title 37, Code of Federal Regulations, §1.56 which occurred between the filing date of the prior application and the national or PCT international filing date of this application:

APPLICATION SERIAL NO.	U.S. FILING DATE	STATUS: PATENTED, PENDING, ABANDONED

And I hereby appoint Michael R. Davis, Reg. No. 25,134; Matthew M. Jacob, Reg. No. 25,154; Warren M. Cheek, Jr., Reg. No. 33,367; Nils Pedersen, Reg. No. 33,145; Charles R. Watts, Reg. No. 33,142; and Michael S. Huppert, Reg. No. 40,268, who together constitute the firm of WENDEROTH, LIND & PONACK, L.L.P., as well as any other attorneys and agents associated with Customer No. 000513, to prosecute this application and to transact all business in the U.S. Patent and Trademark Office connected therewith.

I hereby authorize the U.S. attorneys and agents named herein to accept and follow instructions from Bryn & Aarflot AS as to any action to be taken in the U.S. Patent and Trademark Office regarding this application without direct communication between the U.S. attorneys and myself. In the event of a change in the persons from whom instructions may be taken, the U.S. attorneys named herein will be so notified by me.

Direct Correspondence to Customer No:



000513

PATENT TRADEMARK OFFICE

Direct Telephone Calls to:




WENDEROTH, LIND & PONACK, L L P
2033 "K" Street, N.W., Suite 800
Washington, D.C. 20006-1021

Phone (202) 721-8200
Fax (202) 721-8250

Full Name of First Inventor	FAMILY NAME <u>OLSBYE</u>	FIRST GIVEN NAME <u>Unni</u>	SECOND GIVEN NAME
Residence & Citizenship	CITY <u>Oslo</u>	STATE OR COUNTRY <u>Norway</u>	COUNTRY OF CITIZENSHIP <u>Norway</u>
Post Office Address	ADDRESS <u>Agronomveien 7B, N-1187 Oslo, Norway</u>	CITY	STATE OR COUNTRY ZIP CODE
Full Name of Second Inventor	FAMILY NAME <u>AKPORIAYE</u>	FIRST GIVEN NAME <u>Duncan</u>	SECOND GIVEN NAME
Residence & Citizenship	CITY <u>Oslo</u>	STATE OR COUNTRY <u>Norway</u>	COUNTRY OF CITIZENSHIP <u>Great Britain</u>
Post Office Address	ADDRESS <u>Kristine Bonneviens v. 15, N-0592 Oslo, Norway</u>	CITY	STATE OR COUNTRY ZIP CODE
Full Name of Third Inventor	FAMILY NAME <u>RYTTER</u>	FIRST GIVEN NAME <u>Erling</u>	SECOND GIVEN NAME
Residence & Citizenship	CITY <u>Trondheim</u>	STATE OR COUNTRY <u>Norway</u>	COUNTRY OF CITIZENSHIP <u>Norway</u>
Post Office Address	ADDRESS <u>Steinåsen 19, N-7049 Trondheim, Norway</u>	CITY	STATE OR COUNTRY ZIP CODE
Full Name of Fourth Inventor	FAMILY NAME <u>RØNNEKLEIV</u>	FIRST GIVEN NAME <u>Morten</u>	SECOND GIVEN NAME
Residence & Citizenship	CITY <u>Trondheim</u>	STATE OR COUNTRY <u>Norway</u>	COUNTRY OF CITIZENSHIP <u>Norway</u>
Post Office Address	ADDRESS <u>Tingveien 23D, N-7046 Trondheim, Norway</u>	CITY	STATE OR COUNTRY ZIP CODE
Full Name of Fifth Inventor	FAMILY NAME	FIRST GIVEN NAME	SECOND GIVEN NAME
Residence & Citizenship	CITY	STATE OR COUNTRY	COUNTRY OF CITIZENSHIP
Post Office Address	ADDRESS	CITY	STATE OR COUNTRY ZIP CODE
Full Name of Sixth Inventor	FAMILY NAME	FIRST GIVEN NAME	SECOND GIVEN NAME

Residence & Citizenship	CITY	STATE OR COUNTRY	COUNTRY OF CITIZENSHIP
Post Office Address	ADDRESS	CITY	STATE OR COUNTRY ZIP CODE

I further declare that all statements made herein of my own knowledge are true, and that all statements on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code, and that such willful false statements may jeopardize the validity of the application or any patent issuing thereon.

1st Inventor	<u></u>	Unni OLSBYE	Date	<u>20.8.01</u>
2nd Inventor	<u></u>	Duncan AKPORIAYE	Date	<u>20-08-2001</u>
3rd Inventor	<u></u>	Erling RYTTER	Date	<u>13.8.01</u>
4th Inventor	<u>Morten Rønnekleiv</u>	Morten RØNNEKLEIV	Date	<u>13.8.01</u>
5th Inventor	_____	_____	Date	_____
6th Inventor	_____	_____	Date	_____

The above application may be more particularly identified as follows:

U.S. Application Serial No. 09/869,042 Filing Date June 22, 2001

Applicant Reference Number 104501/DD/JE Atty Docket No. 2001_0768A

Title of Invention CATALYSTS CONSISTING OF METALS ON HYDROTALCITE-BASED CARRIER MATERIALS, AND METHOD FOR THE PREPARATION THEREOF